



DATA SHEET DIGITAL PRINTING VINYL PERMANENT ADHESIVE V20ITRI

Polymeric calandered cadmium-free 80 micron PVC film, coated with a pressure sensitive acrylic adhesive. Destined for inkjet printing with solvent, eco-solvent, UV and HP Latex inks. White translucent finish.

SPECIFICATIONS:

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	80	
• Total caliper (µm):	275	
• Total specific weight (g/m ²):	300	HEXGSM001
• Tensile strength (N/25mm):	min. 35	HEXNFX4102I
• Elongation at break (%):	min. 100	HEXNFX4102I
• Dimensional stability (mm): after 168h at 70°C	< 0.4	HEXRET001

GENERAL PRINTER COMPATIBILITIES:

- Inkjet printers with solvent, eco-solvent, UV and HP Latex inks.

LINER:

- Silicone PE paper 145 g/m² grey HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Average values measured while editing the technical data sheet)

• Peel on glass at 180° (N/25mm):		HEXFTM001
20 minutes after application	19	
24 hours after application	23	
• Initial tack (N/25mm):	19	HEXFTM009
• Release (N/25mm):	0.20	HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

RECOMMENDATIONS:

- Touch dry after less than 15 minutes depending on printer used.
- Minimum application temperature +10°C (+50°F).
- Optimum environment -20°C to +60°C (-4°F to +140°F).
- The surface aspect can be advantageously improved by applying the appropriate gloss laminate (V750).
- Optimum drying time before laminating or varnishing is 24 hours.
- Solvent based acrylic adhesive.
- Immediate and permanent adhesion, not repositionable, suitable for wet application.
- Very good adhesion on glass, steel, aluminium, PVC, melamine, ... except grained surfaces or acrylic paints.
- In the case of painted substrates self-adhesive media must only be applied onto the undamaged original paintwork. If the paint is not the original paintwork and/or if it is damaged, the application and the removal are at the installer's risk.

SHELF LIFE:

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

DURABILITY:

- Unprinted vertical outdoor exposure: 5 years.
- Printed and laminated vertical outdoor exposure: 3 years.
- Printed vertical outdoor exposure: 2 years.

Note:

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force.

All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.