

Protac[™] Scribe[™]

Overlaminating Film

Protac[™] Scribe[™] is a 1.6 mil (40μ) biaxially-oriented PP laminating film with a gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with a siliconized PE.

Typical Applications

- Suitable for application to heat sensitive output and high ink coverage images printed on photo gloss paper.
- Ideal for dry erase presentation boards, schedules, yearly planners, or maps.

Product Structure

| | | |
|---------------|--------------------------------------|-----------------|
| Film | Gloss Clear PP | } 2.6 mil (65μ) |
| Adhesive | Aqueous Acrylic (Pressure Sensitive) | |
| Release Liner | Siliconized 1 Side PE Coated Kraft | |

Physical Characteristics

| | |
|------------------------------|--|
| Film Thickness | 1.6 mil (40μ) |
| Adhesive Layer | 1 mil (25μ) |
| Film/Adhesive Ratio | 1.6:1 |
| UV Protection Factor | Not Applicable |
| Outdoor Durability | Not Applicable |
| Service Temperature Range | -4°F to 248°F (-20°C to 120°C) |
| Peel Strength (20 min, FTM1) | 11 N/25mm |
| Shelf Life | Use within 1 year after opening original box |
| Storage Conditions | 59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity |

Process Settings

| Equipment Type | Temperature | Speed |
|------------------|----------------------------------|--|
| Roller Laminator | Room temperature to 104°F (40°C) | 1 ft to 8 ft (0.3m to 2.5m) per minute |
| Press | Not recommended | |

IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein.

Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.