
### Athpol G10: Extruded GPPS





Extruded sheet products which combine the excellent rigidity and clarity from use of a GPPS (crystal PS) polymer.



# **Key Characteristics**

- Excellent transparency (high light transmission)
- Good surface hardness / scratch resistance
- Available in smooth and textured finishes
- Excellent rigidityRange of colour tints available

## Applications

Typical applications include shower cubicle doors and panels (textured translucent panels -TLP's), DIY applications, indoor glazing, picture frames, display stands etc.



# Product Range

Product Code	Product Description	Properties	
Athpol G10	Extruded GPPS (crystal PS) sheet	Excellent clarity; high rigidity; good scratch resistance	

G10 Datasheet.indd 1

#### Technical Information (1)

Property	Test Method	Unit	Athpol G10
Density (2)	ISO 1183 / B	g/cm <sup>3</sup>	1.05
Tensile Strength	ISO 527-2 / 50	MPa	42
Tensile Modulus	ISO 527-2	MPa	3100
Flexural Strength	ISO 178	MPa	75
Charpy Impact Strength (un-notched @ 23°C)	ISO 179 / 1eU	kJ/m²	9
Temp. of Deflection under Load	ISO 75-2 / A	°C	75
Vicat Softening Point	ISO 306 / B50	°C	85
Flammability @ 1.6mm	UL94	Class	НВ
"A" Surface Gloss (60° angle - smooth surface) <sup>(4)</sup>	ISO 2813	Gloss Units	>85

<sup>(1)</sup> Property evaluations based on injection moulded unpigmented samples unless otherwise stated

Where certain requirements are deemed critical, e.g. gloss / matt levels, opacity etc., then these requirements must be communicated to Athlone Extrusions such that the necessary standards are agreed before orders are placed.

## Standard Range

Property	Extruded Sheet	
Gauge:	2.0 - 6.0mm	
Width:	350 – 1250mm	
Length:	500 – 2500mm	
Colour:	available in clear and colour tints	
Surface Finish:	gloss finish	
Textured Finish:	extensive range of textured finishes available	
Optional Extras:		
Protective PE Film	on request (smooth surface)	

### Standard Tolerances

Sheet Thickness (mm)	2.0 to 4.99	5.0 to 6.0
Gauge	+/- 0.1mm	+/- 0.15mm
Width	+/- 1.5mm	+/- 1.5mm
Length	+/- 3.0mm	+/- 3.0mm

Walsh Graphics Cork: +353 (0) 21 452 4744 Unit 1, Hillview Campus, Euro Business Park, Little Island, Cork, T45 V523.



Walsh Graphics Dublin: +353 (0) 1 969 5291 Unit E7, South City Business Park, Tallaght, Dublin 24, D24 NX09.

<sup>(2)</sup> Density values vary with pigmentation

<sup>(3)</sup> All gloss readings are based on thermoformed parts - gloss levels may vary this dependent on sheet gauge