

GRAPHICS - Wide Format Ink Jet Print Media

Issue date : 07/01/2011  
Date last modification : 16/09/2019**4-GL3B-02659 RI-JET 100 GLOSS WHITE AR802 REMOVABLE WK135****Face Material**

Gloss white monomeric vinyl film.

Type	Monomeric vinyl		
Colour and Finish	Gloss white		
Weight	134 g/m <sup>2</sup> ±10%	ISO-536	
Thickness	100 µ ±10%	ISO 534-80	

**Adhesive**

Removable adhesive offering easy and clean removability from glass and from many other substrates. Not recommended on paper, PVC, ABS, PS, air dried paints and varnishes.

Reference	AR802 removable
Type	Acrylic removable
Min. Appl. Temp.	+10°C
Service Temp.	-20°C/+80°C
Tack	7 N/inch <sup>2</sup>
Final Adhesion	8 N/inch

**Liner**

Type	One side siliconised clay coated Kraft		
Colour and Finish	White		
Weight	135 g/m <sup>2</sup> ±10%	PP-032 - ISO 536	
Thickness	132 µ ±10%	ISO 534	
Transparency	n.a. %	DIN 53 147-64	

**Applications**

For advertising and promotional applications (window graphics and outdoor and indoor posters, billboards and signs) and for vehicle applications (flat sided including buses, trams and taxis).

- . Flammability: Self - extinguish (ISO-3795)
- . Outdoor vertical exposure durability: UP TO 3 YEARS. The Durability data are given for unprinted films only and based on Zone 1 exposure conditions (Northern and Eastern Europe, Italy, France).

**Printing Methods**

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing. Also suitable for latex printing. Testing for suitability between media, printers and inks is always recommended prior to use.

**Shelf life**

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

