



ARLON

## ► ProTec Series 3960

### Heavy Duty Overlaminates

ProTec Series 3960 overlaminates is a 12-mil (305 micron) film with a clear, permanent pressure-sensitive adhesive. The heavy gauge product is designed to protect decals and graphics while maintaining high clarity. ProTec Series 3960 is rated for an outdoor durability up to 2 years.

### APPLICATIONS & FEATURES

- Protective overlaminates for racing, dirt bikes, and other recreational vehicles
- Ideal for applications needing exceptional durability and abrasion resistance
- Use in conjunction with Arlon's DPF 8000™ Ultra Tack or DPF 8200 High Tack film
- Designed to be laminated cold without any heat
- Excellent clarity and gloss retention
- Minimize silvering and enhance image quality with fast wet-out adhesive system

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	70 to 90 Gloss Units	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	12-mil (305 micron)	
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 45.67 lb/in	≥ 8.16 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 270%	
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	50°F to 80°F	10°C to 26°C
<b>SERVICE TEMPERATURE RANGE</b>	Film applied to etched aluminum panels 24 hours prior to testing	-40°F to 176°F	-40°C to 80°C
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours, on aluminum panel	20-mil	0.51 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min. 70°F (21°C)	≥ 3.00 lbs/in	≥ 0.54 kg/cm
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	38 g/2 in	7.48 g/cm
<b>HUMIDITY RESISTANCE</b>	Film applied to etched aluminum panels 24 hours prior to testing. 100% relative humidity, 100°F (38°C) for 500 hours.	No Appreciable Effect	
<b>GASOLINE RESISTANCE</b>	Film applied to etched aluminum panels 24 hours prior to testing. Immersed 30 minutes at 70°F (21°C), stabilized for 24 hours before inspection.	No Appreciable Effect	

Standard Terms & Conditions Apply

#### USA

- 200 Boysenberry Lane, Placentia, CA 92870
- 800 232 7161 / +1 714 985 6300
- +1 714 985 6305

#### EUROPE

- Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
- +31 70 354 4311
- +31 70 355 7721

#### CHINA

- No. 1989 Xinchang Road, Weifang, Shandong, 262400
- +86 0536 6226568

## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All orders and purchases made in connection with this document are governed and limited by Arlon's Standard Terms and Conditions, which are incorporated in full by this reference and are available at <http://www.arlon.com/terms-and-conditions> or in hardcopy by request.

September 2020v1

### USA

-  200 Boysenberry Lane, Placentia, CA 92870
-  800 232 7161 / +1 714 985 6300
-  +1 714 985 6305

### EUROPE

-  Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
-  +31 70 354 4311
-  +31 70 355 7721

### CHINA

-  No. 1989 Xinchang Road, Weifang, Shandong, 262400
-  +86 0536 6226568